

Tera 8 WA**100 % Polyester - Continuous Filament Polyester****Applications**

Lifting-, stretcher-, cargo restraint belts, large tarpaulins, shoes, bags, upholsterer work
 Additional finish to ensure a high degree of water repellancy and soil resistance.

Advantages

Very high breaking strength and abrasion resistance for excellent seam strength
 Ideal sewability
 Decorative seams with luster shine
 Non-stick finish
 Permanent finish for water repellent and soil resistant seams which are not affected by repeated washing and dry cleaning.

Make-up

400 m, 1.200 m, 4.000 m

Shade range

Shade card Gütermann Tera/Skala 2003

Needle size

NM 170 to NM 200

Technology

Count No./Tkt. 8 - dtex 3750(3)
 Strength < 16.750 cN
 Extension at break < 17,5 %
 Boiling shrinkage below 2 %
 Thermal shrinkage below 3 %

Fastness

Fastness to water in accordance with DIN 54006 = grade 4 and better
 Fastness to perspiration in accordance with DIN 54020 = grade 4 and better
 Fastness to rubbing in accordance with DIN 54021 = grade 4 and better
 Fastness to organic solvents in accordance with DIN 54023 = grade 4 and better

