Article information

Gütermann

Tera 10 WA

100 % Polyester - Continuous Filament Polyester

Applications

For distinctive decorative seams as well as heavy-duty holding seams, equipment, technical articles
Additional finish to ensure a high degree of water reppelancy and soil resistence.

Advantages

Ideal sewability; non-stick finish
High breaking strength and good abrasion resistance for durable seams
Permanen finish for water repellent and soil resistant seams which are not affected by repeated washing and dry cleaning.

Make-up	300 m, 1.000 m
Shade range	Shade card Gütermann Tera 2003
Needle size	NM 140 to NM 160
Technology	
Count	No./Tkt. 10 - dtex 2.900(3)
Strength	< 14.400 cN
Extension at break	< 17,5 %
Boiling shrinkage	below 2 %
Thermal shrinkage	below 3 %
Fastness	
Fastness to water	in accordance with DIN 54006 = grade 4 and better
Fastness to perspiration	in accordance with DIN 54020 = grade 4 and better
Fastness to rubbing	in accordance with DIN 54021 = grade 4 and better
Fastness to organic solvents	in accordance with DIN 54023 = grade 4 and better

Gütermann AG, Landstraße 1, DE-79261 Gutach-Breisgau, Tel. +49/7681/21-0, Fax +49/7681/21-449
Perivale-Gütermann Ltd., GB-Hayes, Middlesex UB4 OJR, Tel. +44/20/8589 1600, Fax +44/20/8589 1636
Gütermann Polygal Mexicana S.A. de C.V., MX-Jiutepec, Morelos CP. 62500, Tel. +52/7/320 2100, Fax +52/7/319 0967
Gütermann of America, Inc., US-Charlotte, NC 28241-7387, Tel. +1/704/525 7068, Fax +1/704/525 7071
www.guetermann.com