

Article information



Salta K 40

100 % meta-Aramid (Nomex®) high temperature resistant

	Salta K 40 – No. 40
Applications	For seams requiring a high degree of heat resistance for protective clothing, fire fighters, metal-processing industries, foundries as well as for battle dresses, awnings and equipments.
Advantages	May be subjected to temperatures of up to 360°C for short periods; will not melt. Self-extinguishing when no longer subjected to flame. Good chemical resistance to weak acids and alkalis.
Make-up	
Size	400 m, 4.000 m
Shade range	Shade card Gütermann K/L
Needle size	NM 90 – 110 / 14 – 18
Technology	
Count	No./Tkt. 40 - dtex 750(3) – tex 75
Breaking strength	> 1.950 cN
Elongation	φ 33% (30 – 36%)
Boiling shrinkage (30 min.)	< 1 %
Thermal shrinkage (160°C/30 min.)	< 1 %
Fastness	
Wash fastness	In accordance with ISO 105 CO3 – grade 3-4 and better
Water fastness	In accordance with ISO 105 EO1 – grade 3-4 and better
Rub fastness	In accordance with ISO 105 X12 – grade 3-4 and better
Hypochlorite fastness	In accordance with ISO 105 NO1 – grade 3-4 and better
Dry cleaning fastness	In accordance with ISO 105 DO1 – grade 3-4 and better
Perspiration fastness	In accordance with ISO 105 EO4 – grade 3-4 and better
Light fastness	In accordance with ISO 105 BO2 – grade 2-3 and better
Care instructions	
	www.guetermann.com Gütermann

Nomex® = registered trademark of DuPont™